Homogeneity tests on neutron shield concrete

Koichi Okuno^{1,*} and Hiroshi Iikura²

¹HAZAMA ANDO Technical Research Institute, 515-1 Karima, Tsukuba, Ibaraki, 305-0822, Japan ²JAEA Quantum Beam Science Directorate, 2-4 Shirakata, Tokai-mura, Naka-gun, Ibaraki, 319-1195, Japan (Received June 30, 2013; accepted in revised form November 10, 2014; published online November 20, 2014)

In recent years, neutrons have been studied for application in fields such as material analysis and boron neutron capture therapy. To create a compact shield for these facilities, a neutron shield concrete is developed. Verifying the homogeneity of the concrete is important to ensure adequate shielding performance. In this research, neutron radiography images of the concrete are taken using the Thermal Neutron Radiography Facility (TNRF) of the JRR-3 research reactor, and the transmission ratio of the thermal neutrons were estimated. The results showed that the transmission ratio of the concrete was almost the same at each depth.

Keywords: Neutron, Neutron radiography, Shielding, Concrete

DOI: 10.13538/j.1001-8042/nst.25.S010604

I. INTRODUCTION

In recent years, neutrons have been studied for application in various fields, such as material analysis and boron neutron capture therapy. To create a compact shield for such facilities, a neutron shield concrete that has the same mechanical strength as ordinary concrete has been developed [1]. This concrete contains about 15 wt% of hydrogen and about 3 wt% of B_2O_3 .

It is important to verify the homogeneity of the boron and hydrogen content in the concrete to ensure adequate shielding performance. Therefore, neutron radiography images of the concrete were taken using the Thermal Neutron Radiography Facility (TNRF) of the JRR-3M research reactor and the transmission ratio of the thermal neutrons was estimated.

Visualization of water penetration into concrete through cracks using neutron radiography was reported recently [2], but no application of visualization of homogeneity exists.

II. NEUTRON SHIELD CONCRETE

Neutron shield concrete uses colemanite and peridotite rocks as aggregates. Colemanite is a natural mineral that is rich in boron in the form of B₂O₃. Peridotite is a natural mineral that is rich in hydrogen atoms in the form of H₂O. These aggregate materials, together with ordinary Portland cement, form concrete. Colemanite was used for 10 wt% of the concrete composition to improve the shielding performance and production of the concrete. The density of the neutron shield concrete is the same as that of ordinary concrete. Thus, the neutron shield concrete includes B₂O₃, which has a large capture cross section for thermal neutrons, and abundant H₂O, which slows down neutrons around 2 MeV via elastic scattering. This shield concrete also contains more iron in the form of Fe₂O₃ than ordinary concrete, which slows down highenergy neutrons via inelastic scatterings. These effects provide the concrete with unique shielding performance. Table 1

shows the element analysis for the neutron shield concrete and the ordinary concrete, both of them have the same average density of 2.2 g/cm^3 .

Table 1. Results of density and elemental analysis.

Neutron shield concrete (wt%)					
SiO ₂	H_2O	MgO	MnO	Al_2O_3	
33.1	14.8	29.1	0.09	1.54	
CaO	SO_3	Cl	Cs	Na ₂ O	
11	0.38	0.016	< 0.01	0.05	
TiO ₂	B_2O_3	P_2O_5	Eu	CoO	
0.07	2.61	0.11	< 0.01	< 0.01	
Fe_2O_3	K ₂ O	Ig-loss	Density		
6.23	0.06	13.6	2.2 g/cm^3		
Ordinary concrete (wt%)					
SiO ₂	H_2O	MgO	MnO	Al_2O_3	
57.7	6.04	1.31	0.08	10.5	
CaO	Cs	Na ₂ O	K ₂ O	TiO_2	
14.5	< 0.01	2.29	0.86	0.39	
Fe_2O_3	Eu	Co	Density		
3.47	< 0.01	< 0.01	2.2 g/cm^3		

III. NEUTRON RADIOGRAPHY

Neutron radiography, a non-destructive imaging technique that uses thermal neutrons, is a powerful tool for inspecting materials. The difference between the neutron and X-ray imaging techniques is that X-ray attenuation depends on atomic numbers, whereas neutron attenuation is different for each nucleus. Fig. 1 shows the attenuation coefficient for thermal neutrons [3].

When the neutron beam irradiates a sample, the camera that is located behind the sample takes a picture with black and white contrast. Substantial attenuation of thermal neutrons in elements, such as hydrogen and boron, will cause these neutrons to appear shadowed in the radiographic image. Therefore, while water is not visible in X-ray imaging, it is clearly visible in neutron radiographs because of its high hydrogen content. As shown in Fig. 1, hydrogen, lithium, boron, etc.

^{*} Corresponding author, okuno.koichi@ad-hzm.co.jp



Fig. 1. Attenuation coefficient of each element for thermal neutrons.



Fig. 2. Experimental system of the TNRF.

have a large attenuation ratio, whereas silicon, calcium, oxygen, aluminum, etc. have a small attenuation ratio.

A thermal neutron beam can be found in a research reactor. The TNRF is installed at the JRR-3M research reactor of the Japan Atomic Energy Agency. Table 2 shows the specifications of the TNRF, and Fig. 2 shows its experimental system. In Fig. 2, the thermal neutron beam comes from the JRR-3M and impacts the object. The fluorescent converter is a combination of a scintillator and Gd or ⁶Li. When a thermal neutron is captured by Gd or ⁶Li, the scintillator fluoresces. The fluorescence is scattered by the mirror, and then a photograph or video image is taken with the cold CCD camera.

 Table 2. Specifications of the TNRF

$1.2 \times 10^8 (n/cm^2/s)$
255 mmW×305 mmH
100 μm/pixel
Li-loaded ZnS scintillator

IV. EXPERIMENT

Ordinary concrete and neutron shield concrete were used as experimental samples. As shown in Fig. 3, 20 mm thick slices were obtained from a concrete sample of cylinder with ϕ 100 mm (diameter), starting at the surface and proceeding to greater depths of the core sample, and used for the experiment.

Each sample of sliced concrete was set in front of the fluorescent converter. The experimental setup is shown in Fig. 4.

V. RESULTS AND DISCUSSION

The intensity of the neutron beam that passes through the concrete sample is described by the following equation[4]:

$$I = I_0 \exp\left(-\sum_t T\right),\tag{1}$$

where \sum is the macroscopic cross section, *t* is the sample thickness, *I* is the intensity of the neutron beam that passes through the sample, and I_0 is the incident intensity of the neutron beam.



Fig. 3. (Color online) Concrete sample.



Fig. 4. (Color online) Experimental setup.



Koichi Okuno and Hiroshi Iikura



Fig. 5. Neutron radiography images of transmission ratio at the center line.

S010604-4

HOMOGENEITY TESTS ON NEUTRON ...

The neutron radiography images and the respective transmission ratio of each, measured at a line through their centers, are shown in Fig. 5. In these images, the intensity of the neutrons appears as contrasting black and white. Thus, the intensity can be read as digital bit data. These images were produced from image processing software through digital bit analysis. A transmission ratio of 1.00 (white) means no shielding, while a ratio of 0.00 (black) means complete shielding.

As shown in Fig. 5, the transmission ratio of each concrete sample was almost the same for each depth. No large frequency appears in the graph, which indicates good homogeneity at the center line and, thus, no breaks in the shielding. The transmission ratio of the neutron shield concrete is almost half that of the ordinary concrete, which indicates that the shielding performance is almost twice as good as that of ordinary concrete.

VI. CONCLUSION

Tests on the homogeneity of neutron shield concrete were performed using neutron radiography. The results showed that the transmission ratio of the concrete was almost the same at each depth. Thus, neutron radiography imaging is useful for this type of investigation.

The result of this study is still qualitative. Therefore, the future plan is to develop this study to perform quantitative analysis and accurate estimation.

[1] Koichi O, Masayoshi K, Hitoshi Y, Development of Novel Neutron Shielding Concrete, Nucl Technol, 2009, **168**: 545–552.

evaluation of concrete structures, 2006, 69-76.

- [3] Domanus J C. Neutron Radiography Handbook, D. Reidel Publ. Co., Dordrecht, 1981.
- [4] Hawesworth M R. Neutron Radiography: Equipment and Methods, Atom. Energy Rev, 1977, 15: 169–220.

^[2] Manabu K, Ippei M, Takafumi N, *et al.* Visualization of water penetration into concrete through cracks by neutron radiography, Proc. of International Seminar on durability and lifecycle